

(12) UK Patent Application (19) GB (11) 2 319 024 (13) A

(43) Date of Printing by UK Office 13.05.1998

(21) Application No 9803042.2

(22) Date of Filing 13.08.1996

(30) Priority Data

(31) 233295

(32) 15.08.1995

(33) US

(86) International Application Data

PCT/US96/13137 En 13.08.1996

(87) International Publication Data

WO97/06910 En 27.02.1997

(51) INT CL⁶

B22F 1/00 9/06 , C01D 13/00 15/00 , C07F 1/00 1/02

(52) UK CL (Edition P)

C1A AG44 AG49 AG50 APG1C

(56) Documents Cited by ISA

WO 94/19100 A

US 2798831 A

US 5332533 A

US 3293313 A

US 2058503 A

(58) Field of Search by ISA

INT CL⁶ B22F , C01D , C07F

(71) Applicant(s)

FMC Corporation

(Incorporated in USA - Delaware)

1735 Market Street, Philadelphia, Pennsylvania 19103,
United States of America

(72) Inventor(s)

Bob Troy Dover

Conrad William Kamienski

(72) cont

Robert Charles Morrison

R. Thomas Currin Jr

James Anthony Schwindeman

(74) Agent and/or Address for Service

Baron & Warren

18 South End, Kensington, LONDON, W8 5BU,
United Kingdom

(54) Alkali metal dispersions

(57) A process for producing dispersions of atmospherically stable, coated alkali metal particles and atmospherically stable, coated alkali metal powders by agitating a mixture of molten alkali metal in a hydrocarbon oil at dispersion speeds, optionally in the presence of a dispersing agent, contacting the molten alkali metal-hydrocarbon oil dispersion, above or below the surface of the dispersion, with up to 3 weight percent anhydrous carbon dioxide while agitating the dispersion for at least 1 minute. The dispersion in oil can be used directly in chemical reactions. The bulk of the oil can be removed from the dispersions to produce oil wet particles, the oil wet particles can be washed with a low boiling hydrocarbon to produce hydrocarbon wet particles which can be dried to produce atmospherically stable powders of coated metal particles. The dispersed particles in oil, the oil wet particles, the hydrocarbon wet particles and the atmospherically stable powders can each be used in chemical reactions. After washing and drying, the process produces lithium powders having a surface coating composition containing 0.1-0.3 atom percent lithium, 0.3-0.4 atom percent carbon, and 0.3-0.5 atom percent oxygen. The products of the invention may be used to synthesize organometallic compounds having low color and low soluble inorganic chloride levels.

GB 2 319 024 A

THIS PAGE BLANK (USPTO)

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B22F 1/00, 9/06, C01D 13/00, 15/00, C07F 1/00, 1/02	A1	(11) International Publication Number: WO 97/06910 (43) International Publication Date: 27 February 1997 (27.02.97)
(21) International Application Number: PCT/US96/13137 (22) International Filing Date: 13 August 1996 (13.08.96) (30) Priority Data: 60/002,332 15 August 1995 (15.08.95) US (71) Applicant: FMC CORPORATION [US/US]; 1735 Market Street, Philadelphia, PA 19103 (US). (72) Inventors: DOVER, B., Troy; 214 Long Beach Road, Kings Mountain, NC 28086 (US). KAMIENSKI, Conrad, W.; 516 Eastwood Drive, Gastonia, NC 28054 (US). MORRISON, Robert, C.; 1536 Stableview Drive, Gastonia, NC 28056 (US). CURRIN, R., Thomas, Jr.; 1250 Rainey Road, Salisbury, NC 28146 (US). SCHWINDEMAN, James, A.; 2582 Wallace Acres Lane, Lincolnton, NC 28092 (US). (74) Agent: KENNEDY, Robert, M.; FMC Corporation, 1735 Market Street, Philadelphia, PA 19103 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>

(54) Title: ALKALI METAL DISPERSIONS**(57) Abstract**

A process for producing dispersions of atmospherically stable, coated alkali metal particles and atmospherically stable, coated alkali metal powders by agitating a mixture of molten alkali metal in a hydrocarbon oil at dispersion speeds, optionally in the presence of a dispersing agent, contacting the molten alkali metal-hydrocarbon oil dispersion, above or below the surface of the dispersion, with up to 3 weight percent anhydrous carbon dioxide while agitating the dispersion for at least 1 minute. The dispersion in oil can be used directly in chemical reactions. The bulk of the oil can be removed from the dispersions to produce oil wet particles, the oil wet particles can be washed with a low boiling hydrocarbon to produce hydrocarbon wet particles which can be dried to produce atmospherically stable powders of coated metal particles. The dispersed particles in oil, the oil wet particles, the hydrocarbon wet particles and the atmospherically stable powders can each be used in chemical reactions. After washing and drying, the process produces lithium powders having a surface coating composition containing 0.1-0.3 atom percent lithium, 0.3-0.4 atom percent carbon, and 0.3-0.5 atom percent oxygen. The products of the invention may be used to synthesize organometallic compounds having low color and low soluble inorganic chloride levels.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

ALKALI METAL DISPERSIONS

This invention concerns a process for preparing novel alkali metal
5 dispersions and metal powders derived therefrom by melting an alkali metal in an inert liquid hydrocarbon oil medium, agitating the molten metal under dispersion conditions to produce a dispersion, contacting the molten dispersion with carbon dioxide. The dispersion can be recovered by traditional means.

Conventional processes prepare alkali metal dispersions by melting the
10 alkali metal in a hydrocarbon oil and then agitating the molten metal in an inert hydrocarbon oil at dispersion speed in an inert atmosphere, usually argon. Dispersing aids, such as silicon oils, hydrocarbon polymers, ethers, alcohols, organic acids, carbon black, organic salts and so forth are used to facilitate rapid dispersion of the molten metal and development of uniform particle size. The
15 finished dispersion is cooled, optionally separated from the hydrocarbon oil by washing the metal with a hydrocarbon solvent of choice and stored under argon. Unless stored under argon or some other inert, protective medium these alkali metal dispersions, when dry, react with the atmosphere under ambient storage conditions and there will be a loss of reactivity and danger of ignition.

20 An alternative process forces molten alkali metal and argon through a high shear spray nozzle into hexane.

The book "Alkali Metal Dispersions" by Irving Fatt and Marie Tashima, D. Van Nostrand Company, Inc., 1961, contains conventional dispersion process details and lists numerous dispersing aids and equipment. Dispersing equipment
25 which can be utilized to produce the products of this invention is designed to produce a high tangential shear in the alkali metal-hydrocarbon medium mixture and is described in the book by Fatt and Tashima cited above (pp 41-49). Other conventional reaction equipment such as centrifuges or fluid bed reactors do not provide the high tangential shear necessary to produce such metal dispersions and
30 are not recommended.

The present invention provides a process for producing atmospherically stable alkali metal particles comprising heating, in an inert atmosphere, an alkali

metal selected from the group consisting of sodium and lithium in a hydrocarbon oil to a temperature above the melting point of the alkali metal, agitating the metal in hydrocarbon oil mixture, under dispersion conditions, which mixture optionally contains a dispersing agent, contacting the molten metal-hydrocarbon oil dispersion mixture, above or below its surface, for at least one minute while the mixture is being agitated under dispersion conditions, with at least 0.3 weight percent of anhydrous carbon dioxide, based on the weight of the alkali metal and cooling the alkali metal dispersion to below the melting point of the alkali metal to produce coated alkali metal particles dispersed in oil.

10 In accord with the present invention lithium and sodium metal dispersions in hydrocarbon oil are readily prepared by heating, in an inert atmosphere, to above the melting point of the metals, a temperature range of 100 to 240 °C, about 100 to 150 °C for sodium and 180 to 240 °C for lithium vigorously agitating the molten metal-hydrocarbon oil mixture under high tangential shear (dynamic conditions) for
15 sufficient time to produce a dispersion or emulsion of the metal into uniform particles or globules in the hydrocarbon oil. Optionally the dispersion can be prepared by vigorous stirring at dispersion speeds in the presence of a dispersing agent, then contacting the dispersed metal with anhydrous carbon dioxide gas while maintaining the high tangential shear stirring at dispersion speeds for a
20 certain period of time, at least about a minute, to provide a predetermined amount of the gas for contact and reaction with the metal. Varying the amount of dispersing agent makes it possible to produce particles having different particle size ranges.

Typical alkali metal dispersing or "emulsifying" devices, in use commercially,
25 employ high tangential shear during agitation according to Fatt and Tashima (p 49). The anhydrous carbon dioxide of this invention is added to the molten metal dispersion mixtures of this invention, while the mixtures are under high tangential shear agitation, until 0.3-5 weight percent carbon dioxide based on alkali metal has been introduced into the mixture. While carbon dioxide is preferably introduced
30 below the surface of the mixture, the vigorous agitation conditions necessary to produce dispersions generally gives adequate contact with carbon dioxide introduced in the gas space above the dispersion mixture. The amount of carbon dioxide introduced should be between 0.3 - 5 weight percent based on the metal.

Higher levels of anhydrous carbon dioxide can be employed but do not appear to provide additional advantages. Some minimum contact time between the anhydrous carbon dioxide and metal is necessary, one minute being adequate, and 1 to 5 minutes a practical reaction period. Although, according to US Serial
5 number 08/210,840, one may prepare these dispersions using anhydrous carbon dioxide alone (no dispersing agent present), better control of the metal particle sizes and their size distribution is obtained if one first disperses the metal in the presence of a suitable dispersing agent, and then afterwards adds the anhydrous carbon dioxide under high tangential shear conditions.

10 An advantage of the process is that the anhydrous carbon dioxide unexpectedly reacts sufficiently with molten alkali metals, in particulate or very small molten globule form, suspended in a hydrocarbon oil to form a protective, dispersive coating around the metal particles. This is an unexpected result since Markowitz, discussed below, reports that anhydrous CO₂ does not react with dry
15 100-125 sieve lithium metal particles (125-150 microns) up to 250 °C under static conditions and only slightly with wet CO₂ under these conditions. We have found no such impedance to the reactivity of anhydrous carbon dioxide with lithium metal under the conditions of the present process. Wet CO₂ is not desirable since it generates hydrogen which may react with lithium metal to produce lithium hydride
20 or may be liberated from the vessel as a dangerous gas.

It is another object of this invention to prepare organoalkali compounds, such as organolithium compounds, by utilizing the alkali metal dispersions and alkali metal powders produced by the process of this invention. These organolithium compounds may be alkyllithiums and aryllithiums, lithium
25 dialkylamides, lithium cycloalkylamides, and lithium alkoxides .

Another unexpected advantage of the process is that the large (1-3%) amount of dispersing agent, e.g., oleic acid, ordinarily required to maintain the metal particles at a desired particle size of 10-50 microns, is not required when anhydrous carbon dioxide is added in the process afterwards. Generally, amounts
30 of oleic acid required to achieve this particle size range when CO₂ is employed are less than one percent.

On cooling the dispersions produced by this invention to ambient temperature and removing the hydrocarbon oil medium by washing the metal particles with a low boiling hydrocarbon of choice and evaporating said low boiling hydrocarbon under a stream of dry argon, a lithium (or sodium) metal powder is produced. These powders are relatively unreactive to the components of the ambient atmosphere and can be transferred through such ambient atmospheres from one container to another without danger of ignition or loss of chemical reactivity. The alkali metal powders of this invention are unexpectedly reactive to a number of organic compounds. Conventionally produced alkali metal powders exposed to the ambient atmosphere are well known to react quickly with the components of the atmosphere, rapidly losing activity and occasionally igniting.

Although Markowitz , Journal of Chemical and Engineering Data, Vol. 7, No.4 , p. 590, states that "lithium carbonate, probably formed by the over-all reaction,



yields a protective coating on the surface of the metal", he was not able to react dry carbon dioxide (no moisture present) with 100 - 125 sieve (125-150 micron) lithium particles up to a temperature of 250 °C (no indication given that any reaction with CO₂ occurs above 250 °C) whereas the present process readily reacts dry CO₂ with a molten lithium metal dispersion in hydrocarbon oil at much lower temperatures (190-210 °C). Further, it should be noted that a temperature of 250 °C or higher is not recommended for metal dispersion preparations since generally considerable decomposition of the hydrocarbon oil can occur. In contradistinction to the present process, the lithium metal particles used by Markowitz were previously freed of the mineral oil dispersing medium by washing with hexane and drying in a stream of argon (pp 586-587) before being subjected to contact with dry or wet CO₂ (Markowitz obviously carries out this prior washing of the metal particles because he believes that no reaction with the components of the atmosphere, such as CO₂, can occur in the presence of a hydrocarbon oil (see page 586, second column) since, before x-ray identification of his lithium metal species he mixes each sample with lithium-treated vaseline, a hydrocarbon oil analog, to prevent atmospheric attack on the lithium metal). Furthermore, this contact of metal particles with CO₂ in the Markowitz process took place under static conditions. (It should be noted

that, under such static conditions, the lithium metal particles of the Markowitz process will fuse into a solid mass above the melting point of the lithium metal (183 °C), whereas the lithium metal particles of the present process will retain their original size to much higher temperatures (> 200 °C).

5 Markowitz does not speculate on the reactivity of Li_2CO_3 - coated lithium metal particles with organic substrates nor does he even identify the nature of any coatings on his carbon dioxide-treated lithium metal particles.

 The surface coating on the lithium metal powders produced by the process of this invention has been found by X-ray photoelectron spectroscopy (XPS) to
10 consist of 0.19-0.22 atom percent lithium, 0.33-0.39 atom percent carbon and 0.36-0.46 atom percent oxygen. These ranges for the atomic components do not correspond to those for pure lithium carbonate (Li= 0.33 at %, C= 0.17 at%, O= 0.50 at %). D.J. David, M.H. Froning, T.N. Wittberg, W.E. Moddeman, Applications of Surface Science, 7 (1981) 181-185, state that the results of the reaction of
15 anhydrous carbon dioxide with freshly cut surfaces of lithium metal at ambient temperature (as determined by Auger Electron Spectroscopy) indicate the surface coating to consist of lithium oxide and lithium carbide, not lithium carbonate. At this point, it is not possible to say, definitively, what is the nature of the compounds comprising the protective surface coating on the alkali metal powders of this
20 invention. Some compositional ranges of these elements on the surface of the lithium metal powders of this invention are 0.1-0.3 atom percent lithium, 0.3-0.4 atom percent carbon and 0.3-0.5 atom percent oxygen.

 The process of this invention produces alkali metal dispersions having metal particle sizes in the range of 10 to 300 microns, and even larger sized metal particle
25 powders (to 1000 microns) can easily be produced. On cooling, the resulting alkali metal dispersions of this invention are readily filtered to remove the bulk of the dispersant hydrocarbon oil and the metal is then washed with hexane to remove residual oil, after which the metal powder is dried. The process can be controlled to produce various particle size ranges, such as 10 to 50 microns, 10 to 300 microns,
30 50 to 400 microns, 10 to 1000 microns, and so forth. Surprisingly, the resulting dried metal powders ("Dry Pack") are unexpectedly stable to ambient atmosphere for periods up to about an hour allowing their safe transfer in such atmospheres

from one container to another. The lithium and sodium powders of this invention have been found to be non-pyrophoric by standard pyrophoricity tests.

Lithium metal particle sizes in the inventive dispersions, prepared in the hydrocarbon oil of choice, can be varied by adjusting the amount of dispersing agent (oleic acid) employed, as shown in the tables below .

	Lot no.	O.A.(%)	CO ₂ (%)	Particle Range	Av. Particle Size
	10216	0.450	1.5	5-60	30
	10009	0.346	1.5	10 - 300	80
10	10005	0.184	1.5	100-300	150
	10027	0.171	1.7	50-700	300
	10043	0.151	2.0	400-2000	1000

Notes: (a) Particle ranges and sizes in microns

15 (b) O.A. = Oleic acid (commercial grade)

(c) (%) of O.A. and CO₂ based on lithium metal.

It was found that the use of 0.368% oleic acid alone, i.e., in the absence of CO₂, resulted in agglomeration of the metal in the particular low viscosity hydrocarbon oil of choice under the particular dispersion conditions employed above. Generally, at least about one percent oleic acid is required to produce a satisfactory dispersion with particle sizes under 100 microns in size. The use of CO₂ alone, i.e., no oleic acid present, gave a somewhat broader range of particle sizes and did not allow for any significant variation in the particle size range, as seen in Tables 3 and 4 (compare to above table). Of course, carbon dioxide can be employed with conventional dispersing agents such as oleic acid and generally, one may employ considerably less oleic acid when using CO₂.

Sodium metal, incorporated in the lithium must be kept below the alloy composition, i.e., below 0.88 wt %, in order to prevent thickening or gellation of the

dispersion mass during the preparation of conventional lithium dispersions e.g., using oleic acid alone. However, with the substitution of carbon dioxide for part or all of the oleic acid, there is no practical upper limit for sodium incorporation. For example, Table 2 shows a 5 weight sodium incorporation, based on lithium, which has no tendency to thicken.

A variety of hydrocarbon oils may be used successfully in the present invention. The term hydrocarbon oil, as used herein, includes various oily liquids consisting chiefly or wholly of mixtures of hydrocarbons and includes mineral oils, i.e., liquid products of mineral origin having viscosity limits recognized for oils and hence includes but is not limited to petroleum, shale oils, paraffin oils and the like. There are many manufacturers of these useful hydrocarbon oils. Among these useful hydrocarbon oils are white oils (highly refined), such as, e.g. hydrocarbon oils like Penetec, manufactured by Penreco Division of Pennzoil Products Inc., which has a viscosity in the range of 43-59 pascal-sec at 100°F and a flash point of 265°F (129°C), Parol 100, which has a viscosity of 213-236 pascal-sec at 100°F and a flash point of 360 °F (182°C) and Carnation white oil (viscosity = 133-165 pascal-sec at 100°F; flash pt = 177°C) made by Sonneborn Div. of Witco. Even certain purified hydrocarbon solvents which boil in a range encompassing the melting point of lithium or sodium metal may be used, such as UNOCAL's 140 Solvent (b.p. range = 190-203°C). In addition, unrefined oils, such as Unocal's 460 Solvent (b.p. range 189-262°C), Hydrocarbon Seal oil (b.p. 270-321°C) and Exxon's Telura 401 (b.p. 174-322°C) and Telura 407 (b.p. 245-450°C) may also be used.

Solvents useful in the practice of this invention include aliphatics, especially lower alkanes containing 5 to 10 carbon atoms, aromatics containing 6 to 10 carbon atoms and mixtures thereof including petroleum ether and other commercially available mixtures of hydrocarbons having rather narrow boiling ranges.

Coated lithium particles of this invention can also be prepared by spraying (using a high shear nozzle) molten alkali metal into a carbon dioxide atmosphere, as into a container having a carbon dioxide atmosphere, and collecting the particles in a solvent such as hexane.

The metal powders of this invention can be dried and packaged in suitable containers under an inert atmosphere, such as argon ("Dry PAcK"). The powders can easily be introduced into commercial or laboratory reactions as dry powders or slurried in an inert solvent and introduced into the reaction as a slurry. The
5 dispersions are of course useful in chemical reactions as dispersions in oil, as oil wet particles after filtering to remove the bulk of the oil, or solvent wet particles obtained by washing the oil wet particles with a suitable hydrocarbon solvent to produce solvent wet particles.

It was further unexpectedly found that the coating on the alkali metal
10 particles produced by the process of this invention did not retard the reactivity of the metal with alkyl halides, but did protect the alkali metal from reaction with the ambient atmosphere. It was found that n-butyllithium could be prepared in an 82% yield from such a lithium powder that had been exposed to an ambient atmosphere for a 1 hour period. One might conjecture that a such a protective coating would
15 prevent reactions with such organic substrates from occurring since much smaller molecules, such as oxygen and nitrogen, do not react readily with the coated powders. However, it was found that a normally produced lithium powder (no CO₂), when exposed to the ambient atmosphere for one hour and then reacted with n-butyl chloride, resulted in only a 39 % yield of n-butyllithium. This is an unexpected
20 advantage of producing alkali metal dispersions and powders by the process of this invention since, as here indicated, reaction with the ambient atmosphere lessens the degree of reactivity of alkali metal dispersions, produced by conventional means, with alkyl halides.

Thus, the lithium dispersions and dried lithium powders of this invention
25 unexpectedly have been found to be capable of forming a variety of organolithium products in good yields from corresponding organic chlorides and organoamines. Among these organolithiums are n-, sec-, iso- and tert-butyllithiums, phenyllithium, n-hexyllithium, and 2-ethylhexyllithium. Even lithium dialkylamides such as lithium diisopropylamide could be prepared by metalation of the corresponding
30 dialkylamines (see Table 1). Other organic compounds are also capable of reacting with the metal powders of this invention, such as e.g., alcohols, esters, aldehydes and ketones.

Lithium powder, generated by the process of this invention, protected from ambient conditions and stored under argon for 30 days, produced high (90-95%) yields of n- and sec-butyllithium in hydrocarbon solutions and such n- and sec-butyllithium possessed remarkably low color, platinum-cobalt colors (APHA) of <25 to <100. Tables 1 and 2 list a number of organolithium compounds prepared from the lithium dispersions and powders of this invention and their yields, chloride content, and color. The Pt/Co colors of <25 to <100 are to be compared to typical values of Pt/Co values of 150-250 for typical production run n-butyllithium. The color of the products having colors of <25 upon concentration to 97 weight % by removing most of the hexane only had a color of 50 Pt/Co.

An additional advantage in the use of carbon dioxide coated lithium metal powders is the striking effect on the chloride content of the organolithium solutions in hydrocarbon solvent media (prepared from organic chlorides) when using the lithium metal dispersions prepared by the process of the invention. The values for the soluble inorganic chloride in these solutions are substantially lower than produced by a conventional lithium dispersion. The soluble inorganic chloride from the present invention varies from <100 to <1000 ppm, depending on whether n-butyllithium or s-butyllithium is being made and the concentration of the alkyllithium solution. The same products produced from lithium metal dispersions that do not contain a coating composition of this invention are higher, in the range of 300 ppm and higher. Lower chloride levels are associated with clearer product alkyllithium solutions which have enhanced marketability (see Table 2).

The following examples further illustrate the invention.

25

Example 1

LITHIUM DISPERSION IN PENETECK WHITE HYDROCARBON OIL
USING CARBON DIOXIDE (SURFACE FEED) AS DISPERSING AGENT
Experiment No. 7285

Lithium metal 300 g of low sodium grade was charged to a 3 liter stainless steel resin flask reactor with a 4" (10.16 cm) top fitted with a stirring shaft connected to a fixed high speed stirrer motor with a flexible shaft and top and

-10-

bottom heating mantles in a dry atmosphere room under argon. The reactor was then assembled and 2.25 g of sodium metal and 90% g of Penetec* hydrocarbon oil were added. Penetec hydrocarbon oil is a product of Penreco Division of Pennzoil Products Co. The reactor was then heated to 200°C until the lithium and sodium metals became molten. Stirring was maintained gently and intermittently until all the metal was completely molten. Then the mixture was stirred at high speed (10,000 rpm) for 5 minutes. Carbon dioxide, 7.74 g, was charged, surface fed over a 4 minute period while continuing high speed stirring. The high speed stirring incorporated the carbon dioxide into the metal-hydrocarbon mixture. When the carbon dioxide was all added the stirring was stopped, heating mantles removed and the reactor cooled to about 65°C before bottling the product dispersion. The metal particle size range was found to be 10-200 microns.

Details of further examples using the procedure of this example are given in Tables 3 and 4.

COMPARATIVE EXAMPLE USING OLEIC ACID AND CARBON DIOXIDE

Experiment No. 10009

A weight of 12.7 pounds of lithium metal, 0.033 pounds of sodium metal and 34 pounds of Penetec oil were charged to a 15 gallon stainless steel reactor. The mixture was heated to about 190°C and held there until all of the metal became molten. Intermittent stirring was employed to speed the melting process. High speed shear stirring was begun when the metal became completely molten and sustained for two minutes. The stirring rate was then slowed, 20 grams of oleic acid added, and high speed stirring continued for an additional 2 minutes before starting CO₂ addition. A total of 85 grams of CO₂ was added over a 5 minute period, the temperature rising about 30 degrees. When CO₂ addition was complete, stirring was discontinued, the heating source removed, and cooling applied. When the temperature reached 150°C gentle stirring was begun and the temperature lowered to 50°C before pumping the dispersion out of the vessel. A photomicrograph of the dispersion showed a metal particle range of 10 to 300 microns, with an average particle size less than 100 microns.

Example 2

PREPARATION OF DRY LITHIUM POWDER

Experiment No. 7222

5 Lithium dispersion (lot 7218) prepared as in Example 1 above was filtered and washed in an enclosed, sintered glass filter funnel (fine porosity) to remove the hydrocarbon oil medium. Filtration to remove the bulk of the oil occurred rapidly, as did the subsequent hexane washings (3). Finally, the lithium metal residue in the funnel was washed once with n-pentane, filtered, and the funnel heated with a heat
10 gun to remove traces of solvents. The resulting free-flowing powder was transferred from the funnel to a tightly capped storage bottle.

 A pyrophoricity test [Code of Federal Regulations 49- Transportation Section 173.125 and Appendix E (CFR 49)] carried out on this material showed it to be non-pyrophoric. An exposure test (Experiment #7231) carried out on a sample
15 of this dry powder placed on a watch glass and exposed to ambient air conditions; no heat was generated on exposure to the air nor did any color change occur within 8 hours as occurs with normally prepared lithium dispersion powders. There was no odor of ammonia, either, as normally occurs due to nitridation of the metal.

20

Example 3

PREPARATION OF n-BUTYLLITHIUM IN HEXANE USING CARBON DIOXIDE
DISPERSED LITHIUM METAL POWDER PREVIOUSLY EXPOSED TO AMBIENT
AIR

Experiment No. 7271

25 A lithium metal dispersion in Penetec hydrocarbon oil prepared as in Example 1 with carbon dioxide (#7218) was filtered and the metal washed 3 times with hexane, once with n-pentane, and blown dry. A 9.0 gram (1.30 moles) portion of this metal powder was placed in an open Petri dish and exposed to ambient air (80% relative humidity) for approximately one hour. It was then transferred to a
30 reaction flask along with 164 mls of hexane and 5 ml. of a 15 wt % n-butyllithium in hexane conditioner and stirred for about 20 min. before starting a feed of 54.6 g

(0.584 moles) of n-butyl chloride. The reaction proceeded well and, after 2 hours of post addition stirring, was filtered from the by-product lithium chloride and the latter washed three times with a total of 120 mls of hexane. The filtrations proceeded rapidly to give a water white, clear solution of a 15 wt % solution of n-butyllithium in hexane (82.3% yield based on n-butyl chloride). This experiment showed that there was a protective coating on the lithium metal powder sufficient to prevent any significant loss of lithium metal during transfer of the powder in air.

Example 4

LITHIUM DISPERSION IN PENETECK WHITE HYDROCARBON OIL USING CARBON DIOXIDE AS DISPERSING AGENT - SUBSURFACE FEED

Experiment No. 7505

The reactor and apparatus consisted of a 3 liter stainless steel round bottom flask with 4" (10.16 cm) opening, a 4" (10.16 cm) head with stirring shaft fixed therein, and connected to a high speed stirrer motor via a flexible shaft and a fixed argon inlet and a stainless steel sintered sparger disc and top and bottom heating mantles. The sparger disc (2 1/2" [6.35 cm] biscuit type) was fixed directly below the cutting blade of the stirring shaft and was approximately 3/4" (1.8 cm) off the bottom of reactor.

Lithium metal (350.0 grams) was charged to the reactor in the dry atmosphere room. The reactor was assembled and 2.625 g of sodium and Penetec hydrocarbon oil were added. The reactor was then heated to about 200°C and the contents stirred gently until all metal was molten (approx. 30 minutes). Metal and oil were then stirred at high speed (10,000 rpm) for 4 minutes, then carbon dioxide was fed in through the sparger for a period of 2 minutes. Temperature of the reaction rose 11°C (from 191 - 202°C) when the carbon dioxide was charged. At end of the carbon dioxide feed, stirring was stopped, the heating mantle was removed and the dispersion cooled to about 65°C before transferring to tightly capped storage bottles.

Example 5

SECONDARY BUTYLLITHIUM IN CYCLOHEXANE VIA CARBON DIOXIDE
DISPERSED LITHIUM METAL

Experiment No. 7506

5 The reactor and apparatus consisted of a 500 ml, 3 necked Morton flask, a Claisen adapter, 125 ml dropping funnel, a stirring shaft with teflon blade, stirring motor, and a thermometer probe with an electronic read out.

 Lithium metal dispersion (prepared as in Example 1) was hexane washed two times and pentane washed twice and dried with argon. The metal was then
10 weighed and the experiment conducted using 10% excess lithium (14.42 g or 2.078 moles) and 395 milliliters of cyclohexane solvent.

 Cyclohexane was used to transfer the lithium through a transfer tube to the reactor. Conditioner, 5 ml s-butyllithium in cyclohexane, was added and the mixture stirred for 15-30 minutes. One to three mls of sec-butyl chloride was added which
15 raised the temperature from ambient to around 34 °C. When the temperature began to drop, a slow s- butyl chloride feed was started. The sec-butyl chloride was fed over one hour and forty-five minutes adding a total of 87.4g (0.944 moles) and the reaction temperature was maintained between 32-37 °C. The reaction was stirred for 1.5 hours, then filtered through a 500 ml medium fritted filter using inert
20 diatomaceous earth filter aid. The solution filtered very fast (less than 5 minutes).

 The final solution yield was 89.3%, C-bound lithium was 98.2% with less than 10 ppm soluble inorganic chloride ion in solution.

 Further examples are given in Table 4.

25

Example 6

SODIUM DISPERSION IN PENETECK HYDROCARBON OIL USING CARBON
DIOXIDE AS DISPERSING AGENT

Experiment No. 7511

Into a 500 ml Morton flask fitted with a high speed stirrer and gas inlet tube was placed 60 grams of sodium metal and 140 grams of Penetec hydrocarbon oil. The contents of the flask were heated to 108 °C and stirred until all of the metal became molten. The mixture was then stirred at high speed (10,000 rpm) for 3-4 min. and the carbon dioxide gas feed begun. A total of 1.0 grams of carbon dioxide (1.7 wt % based on the metal) gas was fed into the mixture. The temperature of the reaction rose 3°C within the first few seconds of the feed and then held constant for the remainder of the feed. Then, stirring was discontinued and the mixture cooled to room temperature. Part of the resulting dispersion was washed with hexane and pentane, then blown dry with argon to convert it to a dry, free-flowing powder. A small portion of the dry powder was placed on a watch glass in the hood. It did not ignite. It took approximately 10-15 min. before the powder turned white. The CFR 49 pyrophoricity solid test was negative. A photomicrograph of the solid dispersion showed particle sizes in the 1 to 200 micron range with most in the 50-100 micron range.

Example 7

PREPARATION OF n-BUTYLLITHIUM IN HEXANE VIA CARBON DIOXIDE DISPERSED LITHIUM METAL

Experiment No. 7851

The reactor and apparatus was as described in Example 5, plus heating mantle, and reflux condenser.

The lithium metal dispersion prepared as in Example 1 was hexane washed twice and pentane washed once and dried with argon. The metal was then weighed, 12.10g (1.743 moles).

Hexane, 310 milliliters, was used to transfer the lithium through a transfer tube to the reactor. The hexane-lithium mixture was heated to reflux (dry ice/hexane in condenser) and dropwise feed of n-butyl chloride begun. The reaction proceeded instantaneously (refluxing) and the source of heat was removed. Then 73.4g of n-butyl chloride (0.7924 moles) was fed in over a 40 minute period, the reaction heat controlled strictly by the rate of reflux. The

reaction mixture was allowed to cool to ambient (stirring) over a 2.5 hour period. The mixture was filtered and the lithium chloride residue washed three times with hexane (50 ml each) over a 25-30 minute period. The combined filtrate and washings weighed 256.4 grams. A sample of the clear, water white (Pt/Co=<25
5 water white solution) product solution was assayed for total contained alkalinity and found to contain 2.94 meq/gram of solution 18.83 wt% n- butyllithium. The yield of n-butyllithium was 95.2%. Removal of the hexane solvent under vacuum gave a 97 wt % product which was clear and yellow in color (Pt/Co=50 ASTM=D1209). Further examples are given in Table 4.

10 The above results can be compared to a similar run using a lithium dispersion prepared with oleic acid alone as a dispersant (experiment number 7813) where the resulting product solution was yellow (Pt/Co=175) and the concentrated product (97%) was yellow (Pt/CO=300) and the yield was 94.7%.

From the foregoing disclosure and examples it is evident that it is possible,
15 according to the invention, to produce a stable alkali metal powder formed by heating an alkali metal in a hydrocarbon oil to a temperature above the melting point of the alkali metal, agitating the the molten alkali metal, maintaining agitation under conditions sufficient to disperse the alkali metal into small molten particles while contacting the alkali metal with at least 0.3 weight percent of anhydrous
20 carbon dioxide for at least one minute to disperse the molten alkali metal and recovering a stable coated alkali metal powder having particle sizes in the range of 10 to 1000 microns in the form of a dry powder.

Table 1

USES OF LITHIUM DISPERSION MADE WITH CARBON DIOXIDE STABILIZER

	<u>Lot No.</u>	<u>RLi</u>	<u>Init. Agent</u>	<u>% Yield</u>	
5	<u>Remarks</u>				
	7224	n-Butyl	none	94	Dry pack day 1
	7231	n-Butyl	none	90	Dry pack day 6
	7253	n-Butyl	none	91	Dry pack day 32
	7261	s-Butyl	none	92	Dry pack day 1
10	7262	s-Butyl	none	90	Dry pack day 35
	7292	2-Et Hexyl (heptane)	none	42	(a)
	7230	t-Butyl (pentane)	1g sand per g Li	73	(b)
15	7302	Phenyl (DBE)	IPA	94	(c)
	7309	LDA	none	97	(d)
	7288	n-Hexyl	none	88	

(a) Lithium dispersion prepared with oleic acid as dispersant did not initiate in
20 heptane.

(b) Lithium dispersion prepared with oleic acid as dispersant gave an 80% yield.

(c) Run did not initiate on its own

(d) Reaction gave results equivalent to that using lithium dispersion prepared from
oleic acid.

25

DBE dibutyl ether

IPA 2-propanol

LDA Lithium diisopropylamide

Table 2

Effect of Carbon Dioxide Dispersed Lithium on Final Chloride Content of RLi in
Hydrocarbon Solution

5	<u>Run No.</u>	<u>Alkyl lithium</u>	<u>Li Dispersant</u>	<u>Yield %</u>	<u>Soluble Inorg.</u>	
	<u>Color</u>					
	<u>(Pt/Co)</u>		<u>(W %)</u>		<u>Cl. (ppm)</u>	
10	7506	SBL(1)	CO2 (0.9)	89	<10	<25
	7515	SBL	CO2/5% Na	88	<11	<25
	7523	SBL	CO2 (1.3)	87	33	<25
	7525	SBL	CO2 (2.6)	89	41	<25
	7526	SBL	CO2 (3.9)	84	46	<25
15	-----					
	7527	NBL(2)	CO2 (1.4)	89	87	<25
	7529	NBL	CO2 (0.9)	90	126	<25
	7530	NBL	CO2/5% Na	83	58	<25
20	7551	NBL	CO2 (3.2)	87	193	<25
	----	NBL	Oleic Acid (1.0)	----	300(3)	
	175					

(1) Cyclohexane solvent

25 (2) Hexane solvent

(3) Typical value

SBL secondary butyllithium

30 NBL normal butyllithium

-18-

TABLE 3
LITHIUM/CO₂ DISPERSIONS IN PENETEC OIL

EXPERIMENT NO.	REACTOR SIZE	PRE-CUT TIME (Min)	CO ₂ % (WT)*	CO ₂ FEED TIME (Min)	PARTICLE SIZE (Microns)
5					
7174	500 ml 18 g Li	3	---	start to finish	10-200
7179	500 ml 30 g Li	3	5.2	2	20-300
10 7187	500 ml 30 g Li	3	3.0	1	20-300
7218	3l. 355 g Li	4	1.8	3	10-200
15 7283	3l. 300 g Li	10	1.0	1	10-500
7285	3l. 300 g Li	5	2.0	4	10-200
7290	3l. 300 g Li	5	3.0	6	10-500
20 7291	500 ml 30 g Li	9	1.0	0.5	20-300

* Surface feed

TABLE 4
CO₂/LITHIUM DISPERSIONS IN PENETECK OIL

	Dispersions					Alkylolithiums					
	Run No.	% CO2	CO2 g/min	CO2 Time (min.)	T (°C) (feed)	Particle Size	Comments	Run No.	Type	Yield	Filler Rate ml/min
10		<u>SURFACE FEED</u>									
	7283	1.29	3.87	1	11	<200		7523	SBL	87.8	100
	7409	2.20	2.16	3	13	20-300		7470	SBL	86.5	33
	7285	2.58	1.94	4	--	20-300		7525	SBL	89.6	250
15	7430	3.16	5.16	2	68	50-100	irregular shape	7432	SBL	didn't initiate	--
								7445	NBL	89.3	63
	7414 ⁽¹⁾	3.87	5.60	0.25	20	50-200	irregular shape	7428	NBL	89.2	3.3
	7290	3.87	1.93	6	12	50-300	round shape	7526	SBL	84.2	>100
20		<u>SUBSURFACE FEED</u>									
	7505	0.94	1.65	2	11	<250		7506	SBL	89.3	100
	7513	1.01	1.52	2	9	>200	large	7515	SBL	88.5	100
	7497	1.41	1.65	3	13	<150		7500	SBL	87.8	100
25	plant	----	----	--	--	<50		7473	SBL	89.5	100
	⁽¹⁾ 0.5 Liter run										

What is claimed is:

1. A process for producing atmospherically stable alkali metal particles characterized by heating, in an inert atmosphere, an alkali metal selected from the group consisting of sodium and lithium in a hydrocarbon oil to a temperature above the melting point of the alkali metal, agitating the metal in hydrocarbon oil mixture, under dispersion conditions, which mixture optionally contains a dispersing agent, contacting the molten metal-hydrocarbon oil dispersion mixture, above or below its surface, for at least one minute while the mixture is being agitated under dispersion conditions, with at least 0.3 weight percent of anhydrous carbon dioxide, based on the weight of the alkali metal and cooling the alkali metal dispersion to below the melting point of the alkali metal to produce coated alkali metal particles dispersed in oil.
2. The process of claim 1 further characterized by filtering the cooled alkali metal dispersed particles of claim 1 to remove the bulk of the hydrocarbon oil, washing the filtered dispersed particles with a low boiling liquid hydrocarbon to remove the remainder of the oil, and recovering hydrocarbon wet alkali metal coated particles.
3. The process of claim 2 further characterized by drying the hydrocarbon wet alkali metal particles to produce dry alkali metal coated particles in the form of powders.
4. The process of claim 1 characterized in that the coated alkali metal is lithium.
5. The process of claim 1 characterized in that the anhydrous carbon dioxide, in an amount of between 0.3 and 5 weight percent based on the alkali metal, is introduced below the surface of the dispersion of molten alkali metal and hydrocarbon oil mixture while the mixture is being agitated under dispersion conditions.
6. The process of claim 1 characterized in that the anhydrous carbon dioxide is passed through the molten alkali metal-hydrocarbon oil mixture in an amount of between 0.3 and 5 weight percent based on the alkali metal.

7. The process of claim 1 characterized in that the dispersing agent is oleic acid and the amount employed is in the range of 0.1 to 3.0 % based on the alkali metal.

8. Atmospherically stable lithium metal particles having metal particle
5 ranges within the range of 10 to 1000 microns which particles contain a protective surface coating composition.

9. Atmospherically stable coated lithium metal particles formed by heating lithium metal in a hydrocarbon oil to a temperature above the melting point of the lithium metal, agitating the the molten lithium, optionally in the presence of a
10 dispersing agent, maintaining agitation under conditions sufficient to disperse the lithium metal into small molten particles, while contacting the lithium metal-oil dispersion mixture, above or below its surface, with at least 0.3 weight percent of anhydrous carbon dioxide for at least one minute to disperse the molten lithium metal, cooling the dispersion to below the melting point of the lithium metal, to
15 produce alkali metal particles dispersed in oil.

10. The atmospherically stable coated lithium metal particles of claim 9 further characterized by being formed by filtering the dispersed particles in oil to remove the bulk of the hydrocarbon oil, washing the filtered alkali metal particles with a low boiling liquid hydrocarbon to remove residual oil, and drying the particles
20 to recover stable coated lithium metal particles having particle sizes in the range of 10 to 1000 microns in the form of a dry powder.

11. An atmospherically stable, coated lithium metal powder according to claim 10 having particle sizes between 10 and 300 microns in size.

12. The atmospherically stable, coated lithium metal powder of claim 10
25 isolated in a low boiling normally liquid hydrocarbon.

13. Atmospherically stable, coated sodium metal particles formed by heating sodium metal in a hydrocarbon oil to a temperature above the melting point of the sodium metal, agitating the the molten sodium, optionally in the presence of a dispersing agent, maintaining agitation under conditions sufficient to disperse the
30 sodium metal into small molten particles, while contacting the sodium metal in the dispersion mixture, above or below its surface, with at least 0.3 weight percent of anhydrous carbon dioxide for at least one minute, cooling the dispersion to below

the melting point of the sodium, to produce coated alkali metal particles dispersed in oil.

14. The atmospherically stable, coated sodium particles of claim 13 further characterized by recovering the stable, coated sodium particles by filtering the dispersed particles in oil to remove the bulk of the hydrocarbon oil, washing the filtered alkali metal particles with a low boiling liquid hydrocarbon to remove residual oil, and drying the particles to recover stable coated sodium metal particles having particle sizes in the range of 10 to 1000 microns in the form of a dry powder.

15. An atmospherically stable, coated sodium metal powder according to claim 14 having particle sizes between 10 and 300 microns in size

16. The atmospherically stable, coated sodium metal powder of claim 14 isolated in a low boiling normally liquid hydrocarbon.

17. The process of preparing organoalkali compounds by reaction of atmospherically stable alkali metal particles, produced by heating an alkali metal in a hydrocarbon oil to above the melting point of the alkali metal, agitating the mixture under high shear mixing conditions, optionally in the presence of a dispersing agent, contacting the molten dispersion, above or below its surface, with at least 0.3 weight percent of anhydrous carbon dioxide based on the weight of alkali metal, cooling the dispersion to below the melting point of the metal, filtering to remove the bulk of the hydrocarbon oil to produce alkali metal particles while wet with oil with an organic compound selected from the group of organic halides, organic amines and organic alcohols.

18. The process of claim 17 further characterized by washing the alkali metal particles that are wet with oil with a low boiling liquid hydrocarbon to produce hydrocarbon wet alkali metal particles, and optionally drying the particles, and reacting the particles with an organic compound selected from the group of organic halides, organic amines and organic alcohols.

19. The process of preparing organolithium compounds by reaction of atmospherically stable lithium metal powders having particle sizes between 10 and 1000 microns in size and having an atmospherically protective surface coating composition with an organic compound selected from group of organic halides, organic amines and organic alcohols.

20. The process of claim 19 characterized in that the alkali metal particles are particles of lithium.

21. The process of claim 19 characterized in that the organic halides are alkyl chlorides and aryl chlorides.

5 22. The process of claim 21 characterized in that the alkyl chlorides are selected from the group consisting essentially of n-butyl chloride, sec.-butyl chloride, isobutyl chloride, t-butyl chloride, hexyl chloride and octyl chloride and the aryl chloride is chlorobenzene.

10 23. The process of claim 19 characterized in that the organic amines are primary and secondary amines.

24. The process of claim 23 characterized in that the secondary amines are diisopropylamine, hexamethyleneimine, and hexamethyldisilazane.

25. The process of claim 19 characterized in that the organic alcohols are isopropyl alcohol, tert-butyl alcohol, and 2-methoxyethanol.

15 26. The atmospherically stable, coated sodium metal particles of claim 14 further characterized by washing the metal with a low boiling liquid hydrocarbon solvent, and drying the powder.

20 27. A normal-butyllithium composition characterized by at least 90 weight percent normal-butyllithium, 1 to 10 weight percent hydrocarbon solvent and having a Pt/Co color of less than 100 and insoluble inorganic chloride content of less than 1000 parts per million.

25 28. A normal-butyllithium composition characterized by at least 10 weight percent normal-butyllithium, 1 to 90 weight percent hydrocarbon solvent and having a Pt/Co color of less than 25 and insoluble inorganic chloride content of less than 200 parts per million.

29. A secondary-butyllithium composition characterized by at least 10 weight percent secondary-butyllithium, 1 to 90 weight percent hydrocarbon solvent and having a Pt/Co color of less than 25 and insoluble inorganic chloride content of less than 100 parts per million.

30. The atmospherically stable, coated lithium metal particles of claim 10 further characterized by washing the metal with a low boiling liquid hydrocarbon solvent, and drying the powder.

5

10

INTERNATIONAL SEARCH REPORT

Int. Application No
PCT/US 96/13137

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 B22F1/00 B22F9/06 C01D13/00 C01D15/00 C07F1/00
C07F1/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 B22F C01D C07F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 94 19100 A (FMC CORP) 1 September 1994 see the whole document ---	1-30
A	US 5 332 533 A (SCHWINDEMAN JAMES A ET AL) 26 July 1994 see claims 1,14 ---	17-30
A	US 3 293 313 A (W.L.BORKOWSKI) 20 December 1966 see example 1 ---	17-30
A	US 2 394 608 A (H.R.RAFTON ET AL) 27 October 1936 see claim 3 ---	7
A	US 2 058 503 A (H.R.RAFTON ET AL) 27 October 1936 see claim 1 ---	1-16
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- *&* document member of the same patent family

Date of the actual completion of the international search

21 November 1996

Date of mailing of the international search report

04. 12. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Schruers, H

INTERNATIONAL SEARCH REPORT

Inter national Application No
PCT/US 96/13137

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 2 798 831 A (O.B.WILLCOX) 9 July 1957 see claim 1 -----	1-16

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter nal Application No

PCT/US 96/13137

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9419100	01-09-94	AU-A- 6128994 DE-T- 4491020 GB-A,B 2290537 JP-T- 8505440 US-A- 5567474	14-09-94 21-12-95 03-01-96 11-06-96 22-10-96
US-A-5332533	26-07-94	AU-A- 7208594 BR-A- 9406930 EP-A- 0707588 WO-A- 9501982	06-02-95 10-09-96 24-04-96 19-01-95
US-A-3293313	20-12-66	NONE	
US-A-2394608	12-02-46	NONE	
US-A-2058503	27-10-36	NONE	
US-A-2798831	09-07-57	NONE	

THIS PAGE BLANK (USPTO)